



ZINC-X

CORROSION INHIBITOR



APPLICATIONS

- Auto & Truck Bodies
- Exhaust Stacks, Mufflers & Manifolds
- Fences
- Heating & Air Conditioning Equipment
- Hot Dip Galvanizing Repair
- Metal Roofs & Gutters
- Offshore Drilling Equipment
- Overseas Storage or Shipments
- Pipes and Water Tanks
- Weldments



PROPERTIES

Appearance/Physical State:
Medium Gray Coating

Evaporation Rate:
<1

Flash Point:
<12°F (-11°C) TCC (concentrate)

Non-Volatiles:
43%

Propellant:
Isobutane/Propane

Specific Gravity (water=1):
2.2 – 2.4

V.O.C. Content:
32%, 288 g/L, 2.4 lbs./gal

Two coats of Zinc-X can inhibit rust on steel submerged in salt water for up to 6 months.

MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE : WWW.LPSLABS.COM

PACKAGE

Net Fill
14 oz. (397 grams) aerosol

Part No.
05616

FEATURES

- Zinc rich, galvanized primer and for rust and corrosion protection
- Inhibits rust on steel through galvanic protection
- >99 % zinc purity
- Dries in 10 to 15 minutes
- Meets or exceeds ASTM A-780-93A
- VOC Compliant
- Withstands water temperature up to 212°F (100°C) and continuous dry heat up to 750°F (400°C)
- Easily removed with common paint thinners (i.e. acetone, xylene, toluene, etc.)
- Value Performance

LPS Laboratories • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

Internet Web Site: www.lpslabs.com

©2007 LPS Laboratories • LPS® is a registered trademark of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2197 • Rev. 12/2007